Cleaning and impregnating the canvas



CLEANING NORDIC TIPIS MADE OF COTTON/POLYESTER CANVAS

- Dilute 1 part Acapella Cleaner with 10 parts tepid water.
- Wet the canvas and allow the agent to work for 4-5 minutes.
- Rub with a soft brush.
- Rinse thoroughly and allow the canvas to dry completely.
- If heavily soiled, the concentration of cleaner can be increased or the procedure above can be repeated.

The recommended amount of ready-mixed cleaner depends on the size of the tent and how soiled it is. The table below can be used as a guideline.

CLEANING WITH ACAPELLA CLEANER

Adventure 5	4 dl cleaner + 3 l water
Adventure 7	5 dl cleaner + 4.5 l water
Adventure 9	7 dl cleaner + 6.5 l water
Adventure 15	8 dl cleaner + 7.5 l water
Granit 14	8 dl cleaner + 8 l water
Granit 21	1 cleaner + 11 water
Granit 40	2.5 I cleaner + 22.5 I water
Cirrus 20	1.5 I cleaner + 13.5 I water
Cirrus 28	2 I cleaner + 21 I water
Cirrus 40	3.5 I cleaner + 31.5 I water
Cirrus/Stratus 72	4 I cleaner + 36 I water
Cirrus 200	7 I cleaner + 63 I water

ADDITIONAL IMPREGNATING OF NORDIC TIPIS

For some of the Nordic tipis, the impregnating agent must be diluted with water. In that case, 1 litre of agent must be diluted with 0.2 litres of water.

Use a brush or a roller to apply the agent to the Nordic tipi. Do not use a spray since it will not be as effective; the agent will coat the outside of the fibres instead of being absorbed into the canvas properly.

Apply enough agent to make the canvas fully moist <u>but do not put on more than</u> <u>that</u>. 1 litre of impregnating agent is sufficient for about 6–8 square metres.

The table below can be used as a guideline for how much impregnating agent is needed. Leftover impregnating agent must be protected from frost. It cannot withstand freezing temperatures.



IMPREGNATING

Adventure 5	3 I impregnating agent + 6 dl water
Adventure 7	4 I impregnating agent + 8 dl water
Adventure 9	6 I impregnating agent + 1.2 I water
Adventure 15	7 I impregnating agent + 1.4 I water

Do not dilute the impregnating agent when treating the Nordic tipis below.

Granit 14	9 I impregnating agent
Granit 21	12 I impregnating agent
Granit 40	25 I impregnating agent
Cirrus 20	15 I impregnating agent
Cirrus 28	23 I impregnating agent
Cirrus 40	35 I impregnating agent
Cirrus/Stratus 72	40 I impregnating agent
Cirrus 200	70 I impregnating agent

Footer reference if required 2 of 2